


TECHNICAL DATASHEET

AR 519

Article description	Tolerance +/-		testing method	
	AR 519			
Finished weight (g/m²)	230	5%	DIN EN 12127	
Coating (g/m²)	39	5%	DIN EN 12127	
Aperture size (mmxmm)	warp	weft		
	25,0	30,1	0,2	
Yarn count (yarns/10 cm)	3,75	3,75	0,5	DIN EN 12127
Tensile strength (N/5 cm)				
Original strength	2300	2300	ø	DIN EN ISO 13934-1
Elongation (%)	3,91	3,75		
Coating type	SBR			
Thickness (mm)	-		ISO 4603	
Weave	leno		DIN 61101-1 + DIN ISO 9354	
Standard measurement (cmxm)	100	50		
SGF	50310	Version-Nr.	41519100408	



Our application recommendations are based on empirical values. These recommendations are barred from any liability. Inspection and testing of our goods for the application field has to be effected by the customer itself. Changes of technical values, images and textes reserved. Older versions will be replaced by the new version.



TECHNICAL DATASHEET

AR 519

Packaging		Tolerance +/-
Colour	black	
Core	1005x76x3	
Packing		
Weight rolls (kg)	11,25	+/-5%
Weight pallet (kg)	135	+/-5%
Quantity per unit		
Rolls per box	12	
Rolls per pallet	12	
Boxes per pallet	1	
Box measurement (LxWxH)	-	
Pallet measurement (LxWxH)	-	